

RESIST-U-UPEL-P

Chemical - UPEL-P - 16 bar - S&D - EN12115



SPECIFICATIONS

Application	UPEL-P, the chemical protection hose with a black, conductive UPE liner in accordance to EN 12115 and highest safety standards. Suitable for the transport of acids, alkalis, aqueous solutions of salts, organic compounds (alcohols, esters, ketones, etc.) incl. aromatic substances, chlorinated hydrocarbons and oxidising acids according to our chemical resistance list.			
Feature	The Resist U tube has an extremely low friction coefficient and good abrasion resistance. The used peroxide cured compounds grant excellent temperature resistance and a safe fit to couplings even after several steam cleaning cycles. These new compounds as well the changed helix construction improves significantly the flexibility and reduced bending radius			
Standard/Approval	EN 12115:2021, TRbF 131/2:1992. UPE tube material is in accordance with FDA 21.CFR.177.156.			
Temperature range	Tube depending on the flow medium up to +100°C. Hose flexible down to -35°C. Steam cleaning without pressure up to 130°C / max. 30 min.			
Safety factor	5 : 1 (exceeds EN12115).			
Tube	UPE, black, electrically conductive, smooth.			
Reinforcement	Textile braided, zinc plated double steel wire helix.			
Cover	EPDM, black, resistant to ozone and weather, abrasion resistant, electrically conductive, cloth impression.			
Marking	continuous mylartape, white letters, blue tape: "SEMPERIT (S) RESIST-U Chemie UPEL-16 bar MADE IN EU /////", as well as continuous embossed tape: "SEMPERIT (S) UPEL-F 12115:2021 TRbF 131/2 UPE SD NW PN 16 bar $\Omega/T_xQ/YY$ ".			
Notice	ATTENTION: The temperature of the medium must be lower than its boiling point. ATTENTION: Please refer to the Semperit resistance list or, in case of doubt, contact Semperit. ATTENTION: Continuous use at the peak values reduces the service life. ATTENTION: To ensure the assembly is leakproof, it must be tested according to EN 12115:2021.			



TECHNICAL DETAILS

			0	0			\bigcap	$\widehat{\square}$	<u>II</u>
Article number	Internal-Ø		Wall width	External-Ø	Work. pressure (max.)	Number of inserts	Bending radius (min.)	Weight approx.	Coil length (max.)
	mm	inch	mm	mm	bar		mm	kg/m	m
48364 1960	19.0	3/4	6.0	31.0	16	2	90	0.70	40
48364 2560	25.0	1	6.0	37.0	16	2	100	0.80	40
48364 3260	32.0	1 1/4	6.0	44.0	16	2	125	1.00	40
48364 3865	38.0	1 1/2	6.5	51.0	16	2	150	1.30	40
48364 5070	50.0		8.0	66.0	16	2	200	1.85	40
48364 6380	63.0	2 1/2	8.0	79.0	16	2	250	2.35	40
48364 7575	75.0		8.0	91.0	16	2	300	2.60	40

Vacuum resistance to -0.9 bar

Please note: Before using our products with new or untested media, or for applications that are not clearly indicated in the product information, written advice must be obtained from a specialist dealer or a Semperit application engineer. For safety reasons, all products must be inspected regularly for operational safety and replaced in the event of any damage (especially of the cover) or unusual signs of wear and tear. All products must be stored, handled, and maintained in accordance with all our respective instructions and DIN 7716:1982. The information in our catalogue as well as each individual datasheet is subject to change at any time without notice since we are constantly developing and improving our products and ute to constant technical developments after the latest release date of the catalogue and/or individual datasheets. To always have the latest product and safety information make sure you visit our website (hoses.semperitgroup.com). Additional important general information about the range, choice and safe use of our products can be found a tour website (hoses.semperitgroup.com) and must be followed without exception.

Important notice: Our catalogue and any individual datasheet have been prepared with great care in order to provide you with all the information you need. The information contained therein is based on the state-ofthe-art industrial technology and many years of experience and testing; whenever indicated for a certain product, we also confirm conformity with the resistance requirements of the media listed in ISO TR 7620:2005[E]. However, the individual conditions of storage, maintenance and use decisively affect the safe and durable use of each product. The quality and safety of our products as indicated in the catalogue or individual datasheets are therefore strictly subject to your continuous observance of all specifications and restrictions in our written product information and applicable laws and standards, the specifications regarding resistance to chemicals and our cleaning procedures. We reject any liability for safety issues or other consequences due to improper product choice, maintenance, or handling [e.g. squashing, rupturing, stretching, or filling with non-approved media]. Our products must not be used in airplanes or other aerial vehicles under any circumstance. Products delivered by us to the USA are manufactured according to EN ISO 1307:2008, unless specified otherwise. Our products are not designated for the sale to the general public and do not fulfill the conditions for "GS-certification", unless stated otherwise in the product datasheet.